

Original Varnishes

Full Gloss Yacht Varnish Suitable for power and sail boats



PRODUCT DESCRIPTION

A traditional yacht varnish with UV resistance. Features include excellent flexibility, ease of application, good gloss retention, and non-blooming qualities. A high clarity finish especially suited to lighter colour timbers.

PRODUCT INFORMATION

Colour	YVA202
Finish	High Gloss
Specific Gravity	0.93
Volume Solids	52%
Typical Shelf Life	2 yrs
VOC (As Supplied)	352 g/l
Unit Size	375 ml, 750 ml, 2.5 lt

DRYING/OVERCOATING INFORMATION

	Drying							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Touch Dry	16 hrs		10 hrs		5 hrs		3 hrs	
Overcoating Substrate Temperature								
Overcoated By	5°C (41°F) Min	Max	15°C (59°F) Min	Max	23°C (73°F) Min	Max	35°C (95°F) Min	Max
Original	36 hrs	5 days	24 hrs	4 days	16 hrs	2 days	12 hrs	1 days

APPLICATION AND USE

Preparation

PREVIOUSLY VARNISHED WOOD

In Good Condition Clean the surface with Super Cleaner. Sand smooth with 280-320 grade paper. Remove sanding dust with thinners.

In Poor Condition Remove all previous coatings.

BARE WOOD Ensure that the surface is thoroughly degreased. Sand smooth with 80-180 grade paper and then 280 grade paper. Remove sanding dust by brushing, dusting and wiping. If wiping with solvent then allow to dry completely before applying the first coat.

Priming bare wood: Thin the first coat by 10-15% with Thinner No.1.

Method

Apply a minimum of 3 unthinned coats, more if using a roller. For best results sand smooth between coats with 320-400 grade wet or dry paper. Avoid using direct from the can. Pour the amount you expect to use in a separate container.

Hints

Mixing Stir well before use.

Thinner Brush - YTA800 Thinner No. 1. Spray - Thinner 910 or Thinner 920

Cleaner Thinner No.1

Roller If applying by roller, lay off with a brush or pad otherwise air bubbles may become trapped in the film.

Airless Spray (Professional spray application only) Pressure: 176-210 bar. Tip Size: 1365-1580.

Conventional Spray (Professional spray application only) Pressure: 2-3 bar. Tip Size: 1.1-1.4 mm. Thin 20-25% with Thinner 910 or Thinner 920.

Airmix spray (Professional spray application only) Pressure: 2 bar. Tip Size: 06-113.

For best results sand lightly between coats with 320-400 grade paper. Avoid using direct from the can. Pour the amount you expect to use in a separate container.

Some Important Points

Use above the waterline only. Do not use below 5°C. Avoid painting in direct sunlight. Product temperature should be minimum 15°C and maximum 35°C. Ambient temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/41°F and maximum 35°C/95°F.

Compatibility/Substrates

Suitable for use on all types of wood as long as correct surface preparation has been carried out.

Number of Coats

3 minimum

Coverage

(Theoretical) - 13.0 m²/L per coat

(Practical) - 11.7 m²/L per coat

Recommended DFT per coat

40 microns dry by brush

Recommended WFT per coat

77 microns wet by brush

Please refer to your local representative or visit www.yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2019.



Original Varnishes

Full Gloss Yacht Varnish Suitable for power and sail boats

Application Methods

Brush, Roller, Conventional Spray, Airless Spray, Airmix (Professional spray application only).

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage

GENERAL INFORMATION:

Exposure to air and extremes of temperature should be avoided. For the full shelf life of Original to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION:

Original should be kept in securely closed containers during transport and storage.

Safety

GENERAL:

Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL:

Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Original cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Please refer to your local representative or visit www.yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2019.